

PARTIAL DISCHARGE CHARACTERISTICS OF LOW-DENSITY POLYETHYLENE AND EFFECT OF NANOFILLER USING PULSE SEQUENCE ANALYSIS

Yanuar Z. Arief¹, Mohd Hafizi Ahmad¹, Nor Asiah Muhamad¹, Rudi Kurnianto², Noor Aliaa Awang¹, Rainer Patsch³

Institute of High Voltage & High Current, Faculty of Electrical Engineering,
Universiti Teknologi Malaysia, Johor Bahru, Malaysia

²Department of Electrical Engineering, University of Tanjungpura, Pontianak, Indonesia

³University of Siegen, Germany

yanuar@utm.my

ABSTRACT This paper describes the partial discharge (PD) characteristics in leaf-like type of low-density polyethylene (LDPE) with nano-Magnesium Oxide (MgO) samples which were investigated using the pulse sequence analysis (PSA) method. This method enables to evaluate the individual sequences of PD events in data sets instead of just accumulated data sets as commonly used in investigations of PD characteristics with the conventional methods. The nano-MgO filler amount was 0, 1, 5, and 10%, respectively. The samples were loaded with a ramped AC-voltage $1.14 \text{ kV}_{\text{rms}}/\text{min}$ up to 4096 PD pulses had occurred. The sensitivity was set about 16 pC. The results revealed that the discharge characteristics change during the growth of an electrical tree depending on sample types and filler amount.

1. INTRODUCTION

Polymeric insulating materials such as polyethylene, epoxy, silicone rubber, etc are widely used in electrical power insulation due to their advantages in electrical and mechanical properties. Partial discharge (PD) investigations in polymeric insulation materials have been performed since decades because the application of polymeric materials in electrical power insulation system increased. However, the PD characteristics during electrical treeing, the relevant degradation process in polymeric materials, is still of interest, because the analysis of PD processes is helpful to understand the degradation phenomena and thus can be used for improvement of the materials.

In this research work, PD characteristics in leaf-like type of low-density polyethylene (LDPE) with nano-Magnesium Oxide (MgO) samples were investigated using the pulse sequence analysis (PSA) method. This method enables to evaluate the individual sequences of PD events in data sets instead of just accumulated data sets as commonly used in investigations of PD characteristics with the conventional methods.

In our previous works, investigation on PD characteristics of neat polyethylene (PE) using PSA have been performed (Patsch, R., et. al., 2007a, Patsch, R., et al., 2007b, Arief, Y. Z., et al., 2007c)

2. EXPERIMENT

2.1 Sample Preparation

150 μm thick of leaf-like specimens were used in this research work. A tungsten wire with 50 μm in diameter is utilized as a needle electrode. The needle tip was formed by electrolytic polishing; its tip radius was 2 μm . The tungsten needle was sandwiched between two nanocomposite films and hot-pressed down to 150 μm in thickness. The specimen sheet was fixed between a slide glass and a cover glass by Aron Alfa adhesive (ToaGosei Ltd.). Aluminum foil was applied as a counter electrode at a distance of 0.4 mm from the tip of tungsten needle (Kurnianto, R. et. al., 2006).

The polymeric sample is low density polyethylene (LDPE) with different content of nanocomposite fillers, namely 0, 1, 5, and 10%, respectively. In this work, they

are so called as NC0, NC1, NC5, and NC10, respectively.

2.2 Technique

The samples were loaded with a ramped AC-voltage $1.14 \text{ kV}_{\text{rms}}/\text{min}$ up to 4096 PD pulses had occurred. The sensitivity was set about 16 pC . The pulse signals were automatically stored in a PC. The PD characteristics like discharge rate, phase of PD occurrence, voltage difference at which PD occurred, etc were observed.

The experimental setup for this work is shown in Fig. 1. The apparent PD charge is detected by a coupling device in the loop with the coupling capacitor C_k and sent to a PD detector. A band pass filter with a range $40\text{--}400 \text{ kHz}$ was used in the measurement amplifier. Using an A/D converter, the PD signal is converted and stored in a PC. The time window for the measurement of the oscillating signal was set to about $51.2 \mu\text{s}$ with a pre-trigger time of 10%. Each sample was injecting the high voltage for thirty times. Experimental results were analyzed using Pulse Shape and Pulse Sequence Analysis (PSA).




Fig. 1 Experimental setup for PD measurement.

3. ANALYSIS

Fig. 2 shows the PD charge occurrence number (n) for all sample types. As can be seen clearly from the figure, PD was occurred early in nanocomposite samples, while for neat LDPE, having partial discharge inception voltage (PDIV).

Figs. 3, 4, and 5 show the phase occurrence of PD charge for neat LDPE and LDPE added with MgO nanofiller. There is a slightly difference of phase occurrence at 1st measurement compared to 30th measurement for all sample types.

Fig. shows the discharge intensity in pC for neat LDPE and LDPE added with 10% of MgO nanofiller. It was found that the nanocomposite sample has lower discharge intensity compared to the neat LDPE sample.




Fig. 2 Discharge rate of applied voltage for all sample types.




Fig. 3 Phase occurrence of PD charge for neat LDPE sample.




Fig. 4 Phase occurrence of PD charge for LDPE added with 5wt% of MgO nanofiller sample.




Fig. 5 Phase occurrence of PD charge for LDPE added with 10wt% of MgO nanofiller sample.




Fig. 6 Discharge intensity in pC at 1st measurement.

In general for electrical treeing in polyethylene discharges occur in both polarities of the applied AC-voltage. For discharges in the positive half waves the magnitudes of the discharges are higher, show the 'standard shape', and in most cases only one discharge per half wave occurs. Discharges in the negative half waves are (in general) smaller; the first peak is usually 'standard', while in some cases the shape of the second peak may be changed. In some cases discharges occur with time differences in the region of some ten μ s, and hence more than one discharge are found in the measuring window of about 50 μ s length.

For discharges in the negative half waves electrons are injected from the needle tip that move towards the flat electrode thus reducing the opposing negative field very quickly and thus consecutive negative discharges can occur in the same negative half wave. Only discharges at very high negative voltages are followed by a discharge in the following positive half wave. Discharges in the positive half waves of the applied voltage accelerate electrons towards the needle, thus leaving behind positively charged molecules. While the electrons enter the metallic needle, the positive charges generate a local electric field that modifies the electric field generated from the externally applied voltage. The field of the charged molecules does not change in the time scale of a few tens of ms (Arief, Y. Z., et. al., 2007c).

4. CONCLUSION

The results revealed that the discharge characteristics change during the growth of an electrical tree depending on sample types and filler amount. Furthermore the analysis suggested that space charges around the tip of the needle electrode generated by the PD events play an important role. Compared with the conventional evaluation method on the base of the phase angles of occurrence, the PSA has proven to be one of powerful tool to investigate PD and in order to gain a better understanding of the discharge phenomena in polymeric

insulating materials and other insulation systems. Effect of electrical ageing gives a significant change in PD characteristic in PE

ACKNOWLEDGMENT

The authors thank *Universiti Teknologi Malaysia (UTM)* for the use of facilities and by awarding Research University Grants (RUG) under vote number Q.J130000.2523.11H21.

REFERENCES

- Kurnianto, R.; Murakami, Y.; Houzumi, N.; Nagao, M.; and Murata, Y.; "Some Fundamentals on Treeing Breakdown in Inorganic filler/LDPE Nano-composite Material", Annual Report Conference on Electrical Insulation and Dielectric Phenomena, Kansas City, USA, 2006.
- Patsch, R.; Arief, Y. Z.; Benzerouk, D.; Menzel, J.; "Pulse Sequence and Pulse Shape Analysis –Methods to Analyze Partial Discharge Processes", International Conference on Electrical Engineering and Informatics, Bandung, Indonesia, 2007a.
- Patsch, R.; Arief, Y. Z.; Benzerouk, D.; Menzel, J.; "Space Charges in Polymers and Their Influence on Electrical Treeing", Annual Report Conference on Electrical Insulation and Dielectric Phenomena, Vancouver BC, Canada, 2007b.
- Arief, Y. Z.; Patsch, R.; Benzerouk, D.; and Menzel, J.; "Partial Discharge Characteristics in Polyethylene using Pulse Shape and Pulse Sequence Analysis, International Power Engineering Conference, Singapore, 2007c.



Yanuar Z. Arief was born in Pontianak, Indonesia in 1971. He graduated from Department of Electrical Engineering, University of Tanjungpura, Pontianak, Indonesia in 1994. He received the M.S. degree from the Bandung

Institute of Technology, Indonesia in 1998 and PhD from Kyushu Institute of Technology, Japan in 2006 and conducted a post-doctoral research at Institute of Material & Diagnostic in Electrical Engineering, University of Siegen, Germany. Currently, he is a senior lecturer in Institute of High Voltage and High Current, *Universiti Teknologi Malaysia*, Johor Bahru, Malaysia. His research interest includes the partial discharge detection and degradation phenomena of polymeric insulating material, nanodielectric composite, renewable and biodegradable material as electrical insulation, and high voltage engineering insulation technology.



Mohd Hafizi Ahmad was born in Perak, Malaysia. He received his B. Eng. and PhD degrees in electrical engineering from UTM, Malaysia in 2009 and 2013 respectively. Formerly, he was visiting researcher in the University of Leicester, UK, Sriwijaya University, Indonesia and Tanjungpura University, Indonesia

within 2010 and 2012. He worked as a tutor in the Faculty of Electrical Engineering, UTM from 2009 - 2013. Currently, he works as a senior lecturer in the Institute of High Voltage And High Current, Faculty of Electrical Engineering, UTM. His research interests cover different types of high voltage insulation (solid, liquid and gas), nanodielectrics, insulation performance and breakdown of dielectric material. He is members of IEEE, IEEE DEIS, IEEE PES and IET.



Nor Asiah Muhamad (M'13) is currently a Senior Lecturer in the Institute of High Voltage and High Current at the Faculty of Electrical Engineering, Universiti Teknologi Malaysia since 2003. She finished her Ph.D. degree in 2009 at the University of New South Wales, Australia. She had

earlier received Bachelor degree in electrical and electronic engineering from Universiti Teknologi PETRONAS, Malaysia in 2002 and a Master degree in electrical power engineering from the University of South Australia in 2006. Her research interest in power system equipment monitoring started since 2005 and the main topics related to this interest are insulation diagnosis and new systems for condition monitoring.



Rudi Kurnianto was born in Pontianak, Indonesia on 27 May 1967. He received the B.Eng. degree from Tanjungpura University Indonesia in 1994 and the M.Eng. degrees from Bandung Institute of Technology, Indonesia in 1998 as well as from

Toyohashi University of Technology, Japan in 2005. He is now working towards the D.Eng. degree in the Department of Electronic and Information Engineering at Toyohashi University of Technology. He has been working as a lecturer at Tanjungpura University since 1995. His research interests are in the area of high voltage engineering. He is a member of IEE Japan.



Noor 'Aliaa Awang was born in Kelantan, Malaysia in 1989. She received the B.Eng degree from *Universiti Tun Hissein Onn Malaysia* in 2013 and the M.Eng degree in 2015 from *Universiti Teknologi Malaysia*. She currently pursuing Doctor of

Philosophy degree at Institute of High Voltage and High Current, *Universiti Teknologi Malaysia*. Her research interest includes partial discharge and nanodielectric composite as electrical insulating material.



Rainer Patsch, was born in Lauban, Silesia, Germany in 1944. He graduated in 1969 as a Diplome-Physicist at the J.-W.-Goethe-University in Frankfurt, Germany. In 1980 he got his PhD in **Physics** from the University in Kassel, Germany. From 1969 to 1986 he

was with the **Central Research Institute of AEG**. Main subjects of his work were basic studies on advantages and problems in the use of polymers in high voltage applications, e.g. the influence of electrical and water treeing in power cables, test methods and preventive measures. He was a **Full Professor** and head of the **Institute of Materials & Diagnostics in Electrical Engineering** at the University of Siegen, Germany (1986-2009). Fields of interest are the basic understanding of ageing and degradation processes in insulating materials in power equipment, especially under service and environmental conditions, and the development of **diagnostic** methods to **monitor the ageing of electric equipment**, especially with regard to the influence on reliability and service life.